# data given here is correct as of June 2022 and is subject to change. The Heraeus logo, Heraeus, Conamic and HSQ are trademarks or Stanad trademarks of Haraeus Holding GmbH or its affiliates. Bil richts reserved. For more sneoffic information wist www harae us/conamic-tradema

# Heraeus

# HSQ®-T

## **Characteristics**

- Highest purity
- Zero aluminum synthetic quartz material
- Wide range of geometries and dimensions

# **Applications**

 Leading edge high-end semiconductor batch furnace applications

HSQ®-T is part of Heraeus' new synthetic material family: Neonyx. With Neonyx you can address the increasing challenges and requirements in high-end semiconductor manufacturing.

For next generation batch furnace tools Heraeus HSQ®-T is providing a solution for today's and future leading-edge semiconductor processes. HSQ®-T is made of synthetic raw material minimizing impurity levels in your process environment and ruling out natural variations in today's natural quartz materials.

# **Full Portfolio Product Range**

Heraeus' HSQ®-T ensures highest consistency and purity paired with availability in all industry standard geometries and dimensions for batch furnace tools.



### **Available Dimensions**

Large Diameter Tubes: up to 470 mm outer diameter
Small Diameter Tubes: 2 mm to 90 mm outer diameter
Rods: 2 mm to 40 mm outer diameter
up to 670 mm outer diameter
up to 600 mm length

### **Chemical Purity**

Typical trace elements and OH content in quartz glass (in ppm)

Elements	Li	Na	K	Mg	Ca	Fe	Cu	Al	ОН
HSQ® 300	0.5	0.2	0.3	< 0.03	0.5	0.1	0.01	15	< 30
HSQ®-T	< 0.01	< 0.01	< 0.01	< 0.01	< 0.02	< 0.01	< 0.01	< 0.01	150-200

Germany

### Heraeus Quarzglas GmbH & Co. KG Heraeus Conamic

Kleinostheim, Germany Phone: +49 6181 35-7444 conamic.basematerials.eu@heraeus.com

China

### Heraeus ShinEtsu Quartz (China) Inc.

Pudong, Shanghai, China Phone: +86 21 6867 2266-809 conamic.basematerials.cn@heraeus.com USA

### Heraeus Quartz North America, LLC. Heraeus Conamic

Chandler, Arizona, USA
Phone: +1 678 714-4306
conamic.basematerials.us@heraeus.com

Japan

### Shin-Etsu Quartz Products Co., Ltd.

Shinagawa, Tokyo, Japan Phone: +81 3 6737-0221 division3@sqp.co.jp UK

 ${\it Heraeus\ Conamic\ UK\ Ltd.}$ 

Wallsend, UK
Phone: +44 191 2598-411
conamic.basematerials.eu@heraeus.com

Taiwan

### Heraeus Materials Technology Taiwan Ltd.

Taipei, Taiwan
Phone: +886 2 2627-1111
conamic.basematerials.tw@heraeus.com

Korea

### Heraeus Korea Corporation Heraeus Conamic Anseong Factory

Miyang-myeon, Gyeonggi-do, Korea Phone: +82 31 671-7601 conamic.basematerials.kr@heraeus.com

www.heraeus-conamic.com