

Supuria®

Single-mode fiber compliant with ITU-T G.657.A2 and ITU-T G.652.D

Physical Characteristics:

Clad Diameter:	$125.0 \pm 0.7 \mu\text{m}$
Clad Non-Circularity:	$\leq 0.7 \%$
Core-Clad Conc. Error:	$\leq 0.5 \mu\text{m}$
Coating Diameter (uncolored):	$237 - 247 \mu\text{m}$
Coating-Clad Conc. Error:	$\leq 12 \mu\text{m}$
Tensile Proof Test:	100 kpsi (0.69 GPa)
Coating Strip Force Range:	$1.0 \text{ N} \leq \text{CSF} \leq 8.9 \text{ N}$
Standard Reel Lengths:	50.4 km

Attenuation Characteristics:

	Maximum	Typical
1310 nm	$\leq 0.35 \text{ dB/km}$	$\leq 0.33 \text{ dB/km}$
1385 nm	$\leq 0.31 \text{ dB/km}$	$\leq 0.28 \text{ dB/km}$
1490 nm	$\leq 0.24 \text{ dB/km}$	$\leq 0.21 \text{ dB/km}$
1550 nm	$\leq 0.21 \text{ dB/km}$	$\leq 0.19 \text{ dB/km}$
1625 nm	$\leq 0.23 \text{ dB/km}$	$\leq 0.20 \text{ dB/km}$

Point Discontinuities 1310 nm, 1550 nm $\leq 0.05 \text{ dB}$

Macrobend Performance:

Bending-induced attenuation does not exceed the specified values under the following deployment conditions:

Deployment Condition	Wavelength	Induced Attenuation
1 turn on 7.5 mm radius mandrel	1550 nm	$\leq 0.5 \text{ dB}$
	1625 nm	$\leq 1.0 \text{ dB}$
1 turn on 10 mm radius mandrel	1550 nm	$\leq 0.1 \text{ dB}$
	1625 nm	$\leq 0.2 \text{ dB}$
10 turns on 15 mm radius mandrel	1550 nm	$\leq 0.03 \text{ dB}$
	1625 nm	$\leq 0.1 \text{ dB}$

Environmental Characteristics (at 1310, 1550 and 1625 nm):

- Temperature Cycling (-60°C to $+85^\circ\text{C}$) $\leq 0.05 \text{ dB/km}$
- High Temperature Aging ($85 \pm 2^\circ\text{C}$) $\leq 0.05 \text{ dB/km}$
- Temperature & Humidity Cycling (at -10°C to $+85^\circ\text{C}$, and 95 % RH) $\leq 0.05 \text{ dB/km}$
- Water Immersion ($23 \pm 2^\circ\text{C}$) $\leq 0.05 \text{ dB/km}$
- Dynamic Fatigue Stress Corrosion Parameter $n_d \geq 20$

Attenuation vs. Wavelength:

Range	Reference	Max Difference α
1285 – 1330 nm	1310 nm	$\leq 0.03 \text{ dB/km}$
1525 – 1575 nm	1550 nm	$\leq 0.02 \text{ dB/km}$

The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength by more than the value α .

Other Characteristics:

Zero Dispersion Wavelength λ_0 :	1302 – 1322 nm
Zero Dispersion Slope S_0 :	$\leq 0.090 \text{ ps/nm}^2 \cdot \text{km}$
Fiber PMD Link Design Value:	$\leq 0.06 \text{ ps}/\sqrt{\text{km}}$
Maximum Individual Fiber PMD:	$\leq 0.1 \text{ ps}/\sqrt{\text{km}}$
Mode Field Diameter (1310 nm):	$8.6 \pm 0.4 \mu\text{m}$
Mode Field Diameter (1550 nm):	$9.9 \pm 0.5 \mu\text{m}$
Cable Cut-Off Wavelength λ_{cc} :	$\leq 1260 \text{ nm}$



HERAEUS COVANTICS HEADQUARTERS

Heraeus Quarzglas GmbH & Co. KG

Heraeusstraße 12–14

63450 Hanau

covantics@heraeus.com

covantics.com/contact

www.heraeus-covantics.com

The data in this brochure is subject to change.

The Heraeus logo, Heraeus and Covantics are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.

For more specific information, visit covantics.com/brands.

To learn about our locations, visit covantics.com/locations.